



ROYALÉ TOUCHE

Technical Specification – Royale Touche

Properties	Specified values as per IS: 2046 – 1995, Type S, HGS
Thickness	1.00mm (±0.10mm)
Dimensional stability at deviated temperature - Longitudinal (%) - Transverse (%)	0.55 (Maximum) 1.025 (Maximum)
Dimensional stability at 20°C - Longitudinal (%) - Transverse (%)	0.375 (Maximum) 0.60 (Maximum)
Resistance to dry heat 180°C	Not worse than Grade 4
Resistance to immersion in boiling water - Mass increase (%) - Thickness increase (%) - Appearance	10.0 (Maximum) 11.8 (Maximum) Not worse than Grade 4
Resistance to impact by small diameter ball	20 N (Minimum)
Resistance to cracking	Not worse than Grade 4
Resistance to scratching	2 N (Minimum)
Resistance to staining	Not worse than Grade 5
Resistance to cigarette burns	Not worse than Grade 3
Resistance to steam	Not worse than Grade 4
Resistance to colour change (wool standards) - In Xenon arc light - In enclosed Carbon arc light	Not worse than Grade 6 Not worse than Grade 5
Resistance to surface wear	350 (revolution)
Appearance	Should be free from foreign particles

OLYMPIC DECOR LLP

Office : ONE42, 401, North Tower, Near Jayantilal Park BRTS, Ambli Bopal Road, Ahmedabad - 380054, Gujarat, India

Phone: 079 - 4750 7600 | 079 - 4001 7979 | LLP Identification no. : AAF-9531 | Email: sales@royaletouche.com | website: www.royaletouche.com